



INTERNATIONAL GEMMOLOGICAL INSTITUTE

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING
OF DIAMONDS AND COLORED STONES
EDUCATIONAL PROGRAMS

Expertise issued by I.G.I. s.v.b.o.
Head Office and Laboratories:
1/7 Schuylstraat, 2018 Antwerp - Belgium
Tel. (32-3) 231 68 45 (6 L) - Fax. (32-3) 232 07 58

Number: F2J21883

LABORATORY REPORT (ORIGINAL)

DESCRIPTION:

SHAPE AND CUT:

WEIGHT:

MEASUREMENTS:

PROPORTIONS and FINISH

Table Diameter Percentage	60 %
Crown Height Percentage	13.5 %
Pavilion Depth Percentage	44.5 %
CULET SIZE:	POINTED
GIRDLE THICKNESS:	THICK (FACETED)
FINISH: Polish-Sym/Prop	VERY GOOD / GOOD
CLARITY GRADE (10 x):	INTERNALLY FLAWLESS
COLOR GRADE:	E (0)
FLUORESCENCE:	DISTINCT

NATURAL DIAMOND

ROUND BRILLIANT

0.53 Carat

5.04 - 5.06 x 3.25mm


DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information about the submitted stone.

ANTWERP, February 10, 2000

TO WHOM IT MAY CONCERN.

The symbols do not usually reflect the size of the characteristics.
Red symbols indicate internal characteristics.
Green symbols indicate external characteristics.



COMMENTS:

(significant external details, visible under high magnification, are not mentioned)

Control Department

LABORATORY DIRECTOR, GEMMOLOGIST

SPACE FOR DOUBLE CHECK, CLARITY AND COLOR GRADE

CLARITY GRADE:	Internally Flawless					vs1	vs2	vs1	vs2	s1	s2	p1	p2	p3											
COLOR GRADE:	D+	D	E	F	G	H	I	J	K	L	M	N	O	P	Q	R	S	T	U	V	W	X	Y	Z	FANCY COLOR

PROPORTIONS - MARGIN: $\pm 1\%$
MEASUREMENTS - MARGIN: ± 0.02 mm

The gemmological analysis of diamonds, precious stones and other minerals must be carried out by specialized gemmologists with many years' experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomena.

The identification of the various species and varieties of stones, the distinction between natural and synthetic stones, as well as various treatment methods currently encountered are of very important factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemmological Report is provided upon request of the customer and/or the owner of the gem. By making this Report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guarantee or warranty.

This Report is subject to the terms and conditions set forth above and on reverse.

© 1995