



INTERNATIONAL GEMMOLOGICAL INSTITUTE

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING
OF DIAMONDS AND COLORED STONES
EDUCATIONAL PROGRAMS

Expertise issued by IGI, b.v.b.a.
Head Office and Laboratories
1/7 Schupstraat, 2018 Antwerp - Belgium
Tel (32-3) 231 68 45 (6 L) - Fax (32-3) 232 07 58

Number: F2G56826

LABORATORY REPORT (ORIGINAL)

DESCRIPTION: NATURAL DIAMOND
SHAPE AND CUT: ROUND BRILLIANT
WEIGHT: 0.53 Carat
MEASUREMENTS: 5.16 - 5.18 x 3.21 mm
PROPORTIONS and FINISH
Table Diameter Percentage 61 %
Crown Height Percentage 13.5 %
Pavilion Depth Percentage 44.5 %
CULET SIZE: POINTED
GIRDLE THICKNESS: MEDIUM TO THIN
FINISH: Polish-Sym/Prop VERY GOOD / VERY GOOD
CLARITY GRADE (10 X): INTERNALLY FLAWLESS
COLOR GRADE: D(0+)
FLUORESCENCE: VERY SLIGHT


DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information about the submitted stone.

ANTWERP, June 24, 1998

TO WHOM IT MAY CONCERN,

The symbols do not usually reflect the size of the characteristics.
Red symbols indicate internal characteristics.
Green symbols indicate external characteristics.



COMMENTS:
(Insignificant external details, visible under high magnification, are not mentioned)

Control Department

LABORATORY DIRECTOR - GEMMOLOGIST

SPACE FOR DOUBLE CHECK, CLARITY AND COLOR GRADE

CLARITY GRADE:	Internally Flawless		vs1		vs2		s1		s2		p1		p2		p3	
COLOR GRADE:	D	1+	1	2	3	4	5	6	7	8	9	10	11	12	13	FANCY COLOR
	E	F	G	H	I	J	K	L	M	N	O	P	Q	R	20	

PROPORTIONS - MARGIN: $\pm 1\%$
MEASUREMENTS - MARGIN: ± 0.02 mm.

The gemmological analysis of diamonds, precious stones and other minerals must be carried out by specialized gemmologists with many years' experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomena.

The identification of the various species and varieties of stones, the distinction between natural and synthetic stones, as well as various treatment methods currently encountered are of very important factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemmological Report is provided upon request of the customer and/or the owner of the gem. By making this Report IGI does not agree to purchase or replace the article. Neither IGI nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a warranty or guarantee.

This Report is subject to the terms and conditions set forth above and on reverse.

© 1998