



INTERNATIONAL GEMMOLOGICAL INSTITUTE

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING
OF DIAMONDS AND COLORED STONES
EDUCATIONAL PROGRAMS

Expertise issued by I.G.I. b.v.b.a.
Head Office and Laboratories.
1/7 Schupstraat, 2018 Antwerp - Belgium
Tel. (32-3) 231 68 45 (6 L.) - Fax. (32-3) 232 07 58

DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information about the submitted stone.


Number: F2H34452

ANTWERP, May 19, 1999

LABORATORY REPORT (ORIGINAL)

TO WHOM IT MAY CONCERN.

DESCRIPTION: NATURAL DIAMOND
SHAPE AND CUT: ROUND BRILLIANT
WEIGHT: 1.06 Carat
MEASUREMENTS: 6.50 - 6.61 x 3.99mm
PROPORTIONS and FINISH
Table Diameter Percentage 58.5 %
Crown Height Percentage 13 %
Pavilion Depth Percentage 43 %
CULET SIZE: MEDIUM
GIRDLE THICKNESS: MEDIUM TO THIN
FINISH : Polish-Sym/Prop GOOD / GOOD
COLOR GRADE: NATURAL FANCY BROWN
- - -
FLUORESCENCE: VERY SLIGHT



COMMENTS:

Control Department

LABORATORY DIRECTOR, GEMMOLOGIST

SPACE FOR DOUBLE CHECK, CLARITY AND COLOR GRADE

CLARITY GRADE: Internally Flawless, vvs 1 vvs 2 vs 1 vs 2 si 1 si 2 p 1 p 2 p 3

COLOR GRADE: 0+ 0 1+ 1 2 3 4 5 6 7 8 9 10 11 12 13 14
D E F G H I J K L M N O P Q R S T U V W X Y Z

PROPORTIONS - MARGIN: $\pm 1\%$
MEASUREMENTS - MARGIN: ± 0.02 mm.

FOR FANCY COLORS AND
SHADES, SEE REVERSE

The gemmological analysis of diamonds, precious stones and other minerals must be carried out by specialized gemmologists with many years' experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic stones, as well as various treatment methods currently encountered are all very important factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemmological Report is provided upon request of the customer and/or the owner of the gem. By making this Report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This Report is subject to the terms and conditions set forth above and on reverse.

© 1995